



Cenex Premium #2 ULSD B20
Includes: Ruby Fieldmaster (B6-B20), Roadmaster (B6-B20)

<u>Physical Property</u>	<u>ASTM</u> Method	<u>Specifications</u>	
		Min	Max
Biodiesel Content (% v/v)	D7371	6.	20.
Gravity API	D4052	Report	
Flash, °F, PM	D93	126	
Kin. Viscosity, 104°F, <i>cSt</i>	D445	1.9	4.1
Corrosion Test 3 hrs. at 122°F	D130		#1
Sulfur, Wt. %	D5453 (2)		15 mg/kg
Pour Point, °F	D97		Report
Cloud Point, °F	D2500/D5733		+14 North +20 South
Ash, Wt. %	D482		0.01
Distillation, °F, 760 mm	D86		
90% Recovered			649
End Point		Report	
Water & Sediment, Vol. %	D2709		0.05
Cetane Number	D613/D6890	46	
Carbon Res. 10% Residuum	D524		0.35
Thermal Stability	D6468		
W unit		75	
% reflection or Y unit		82	
Haze (procedure 2)	D4176		2
Lubricity	D6079		460
Acid Number mg KOH/g	D664		0.3
Oxidation Stability, hours	En15751	6	
Water/Sediment % vol	D2709		0.05

Additional information:

Premium Additive Package is present
Specification valid March 1 through September 30
Cloud and pour point max may be higher due to region product is sold
Meets or exceeds ASTM 7467 specification

Document Name: B20 Roadmaster_Fieldmaster
Author: CE
Revision: 2.0
Effective Date: 11/2/2022